



9	Single Flame Source Test	EN 15534-1:2014 Section 9.6.1 & EN ISO 11925-2:2020	Whether the flame tip reaches 150 mm above the flame application point	No	No	No	No	No	No	Pass
			The time when flame tip reaches 150 mm, s	/	/	/	/	/	/	
			Whether ignition of the filter paper occurs	No	No	No	No	No	No	
10	Striker Impacted by a Falling Weight	With reference to ASTM D4226-19e1 Procedure A and client's requirement	Mean failure energy: 13.9J						Pass	
11	Swelling and Water Absorption	EN 15534-1:2014 Section 8.3.1 & EN 317:1993	Test item	Test item Thickness	Width	Length	Pass			
			Mean swelling	0.17%	0.01%	0.02%				
			Max individual swelling	0.21%	0.02%	0.03%				
			Mean water absorption	0.05%						
			Max individual water absorption	0.06%						